

Application Serial No. 10/628,791  
Reply to Office Action of November 18, 2008

RECEIVED  
CENTRAL FAX CENTER PATENT  
JAN 08 2009 Docket: CU-5983

**Amendments to the Claims**

The listing of claims presented below replaces all prior versions, and listings, of claims in the application.

**Listing of claims:**

1. (previously presented) A correction ink for micro defect of a color pattern comprising a coloring agent, monomer having two or more reactivity functional groups in one molecule, polymer and a solvent, wherein an amount of the solvent is from 25% by weight to 70% by weight of the whole ink, a viscosity of the ink is from 40 to 300 mPa•sec, and  $\tau$  value is 0.3 to 1.3 when  $\gamma$  value is 10 and  $\tau$  value is 4.0 to 10.0 when  $\gamma$  value is 100 in the following formula (1):

$$\tau = K \gamma^L \quad \bullet \bullet \bullet \text{ formula (1)}$$

wherein  $0.081 \leq K \leq 0.111$ ,  $0.881 \leq L \leq 0.954$ .

2. – 3. (cancelled)

4. (original) A correction ink for micro defect of a color pattern according to claim 1, wherein static surface tension of the ink at 25° C is 20 mN/m to 45 mN/m.

5. (cancelled)

6. (original) A correction ink for micro defect of a color pattern according to claim 1, further comprising a polymerization inhibitor.

7. (original) A correction ink for micro defect of a color pattern according to claim 1, wherein said polymer is diallylphthalate prepolymer.

8. (original) A correction ink for micro defect of a color pattern according to claim 1, wherein the ink is a correcting black ink containing a red coloring agent, a yellow coloring agent and a blue coloring agent as said coloring agents.

9. (original) A correcting black ink for micro defect of a color pattern according to claim 8, wherein an optical density is 1.0 or more in the measuring wave range of

Application Serial No. 10/628,791  
Reply to Office Action of November 18, 2008

PATENT  
Docket: CU-5983

400 nm to 760 nm when a layer thickness at curing is less than 1.9  $\mu\text{m}$ .

10. (previously presented) A color filter, wherein a micro defect in a color pattern is corrected by filling with cured product of a correction ink for micro defect of a color pattern comprising a coloring agent, monomer having reactivity functional group, polymer and a solvent, wherein an amount of the solvent is from 25% by weight to 70% by weight of the whole ink, a viscosity of the ink is from 40 to 300 mPa $\cdot$ sec, and difference in level between a corrected part by the ink and surroundings thereof is -3  $\mu\text{m}$  to +5  $\mu\text{m}$ .

11. (original) A color filter according to claim 10, wherein a defect in a black matrix pattern is corrected by filling with cured product of the correcting black ink containing a red coloring agent, a yellow coloring agent and a blue coloring agent as coloring agents.

12. – 19. (cancelled)

20. (previously presented) A correction ink for micro defect of a color pattern according to claim 1, wherein an amount of the monitor is from 15% by weight to 65% by weight of the total amount of the correction ink.

21. – 32. (cancelled)

33. (previously presented) A correction ink for micro defect of a color pattern comprising a coloring agent, monomer having two or more reactivity functional groups in one molecule, polymer and a solvent, wherein an amount of the solvent is from 25% by weight to 70% by weight of the whole ink, a viscosity of the ink is from 40 to 300 mPa $\cdot$ sec, the ink is a correcting black ink containing a red coloring agent, a yellow coloring agent and a blue coloring agent as said coloring agents, and an optical density is 1.0 or more in the measuring wave range of 400 nm to 760 nm when a layer thickness at curing is less than 1.9  $\mu\text{m}$ .

34. (previously presented) A correction ink for micro defect of a color pattern

Application Serial No. 10/628,791  
Reply to Office Action of November 18, 2008

PATENT  
Docket: CU-5983

according to claim 33, wherein static surface tension of the ink at 25°C is 20mN/m to 45 mN/m.

35. (previously presented) A correction ink for micro defect of a color pattern according to claim 33, further comprising a polymerization inhibitor.

36. (previously presented) A correction ink for micro defect of a color pattern according to claim 33, wherein said polymer is diallylphthalate prepolymer.

37. (previously presented) A correction ink for micro defect of a color pattern according to claim 33, wherein an amount of the monomer is from 15% by weight to 65% by weight of the total amount of the correction ink.